

PRODUCT DATA SHEET

SikaTack® ASAP+

HOT-APPLIED AUTOMOTIVE GLASS REPLACEMENT ADHESIVE

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1 component polyurethane
Color (CQP001-1)	Black
Cure mechanism	Moisture-curing
Density (uncured)	1.1 kg/l
Non-sag properties	Excellent
Application temperature	Product 75 – 90 °C (167 – 194 °F) Ambient -18 – 49 °C (0 – 120 °F) Substrate -18 – 77 °C (0 – 170 °F)
Skin time (CQP019-1)	12 minutes ^A
Open time (CQP526-1)	7 minutes ^A
Shore A hardness (CQP023-1 / ISO 868)	65
Tensile strength (CQP036-1 / ISO 37)	6.5 MPa (950 psi)
Elongation at break (CQP036-1 / ISO 37)	300 %
Tensile lap-shear strength (CQP046-1 / ISO 4587)	5 MPa (750 psi)
Safe Drive Away Time (cars) according FMVSS 212 (CQP511-1)	See Table 1
Service Temperature (CQP509-1 / CQP513-1)	-40 – 93 °C (-40 – 200 °F)
Shelf life (CQP016-1)	9 months ^B

CQP = Corporate Quality Procedure ^{A)} 23 °C (73 °F) / 50 % r.h. ^{B)} Stored below 25 °C (77 °F)

DESCRIPTION

SikaTack® ASAP+ is an all-in-one modulus, hot-applied, fast curing, high-viscosity polyurethane adhesive designed for use in replacing direct glazed automotive glass parts. When used as directed SikaTack® ASAP+ meets or exceeds the strength requirements outlined in the direct glazing specifications of automobile manufacturers.

PRODUCT BENEFITS

- 30 Minute Safe Drive Away Time (SDAT); tested according to FMVSS 212/208
- All-in-one modulus & non-conductive
- Short cut-off string
- One step pre-treatment for glass

AREAS OF APPLICATION

SikaTack® ASAP+ has been specifically designed for the Automotive Glass Replacement business. It is ideal for mobile and in-shop installations.

This product is to be used by professional, experienced users only. Related process information in this PDS is specifically for Automotive Glass Replacement. For other applications, tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, label and Safety Data Sheet which are available at <http://usa.sika.com/> or on request at tsmh@us.sika.com. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Product Data Sheet, label and Safety Data Sheet prior to product use.

PRODUCT DATA SHEET

SikaTack® ASAP+

Version 01.01 (06 - 2018), en_US

012002210050001100

CURE MECHANISM

SikaTack® ASAP+ cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the reaction proceeds more slowly. More information can be found in the Safe Drive Away Time table that follows.

Rel. Hum.	Temperature (°F)			
	> 0	> 32	> 50	65 - 120
> 90%	30	30	30	30
> 70%	30	30	30	30
> 40%	30	30	30	30
> 20%	30	30	30	30
> 0%	30	30	30	30

Table 1: Safe Drive Away Time (minutes)

CHEMICAL RESISTANCE

SikaTack® ASAP+ is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, sound, dry and free from all traces of traditional and non-traditional contamination. All corrosion must be removed and all bare metal scrapes and scratches must be prepared in accordance with Sika's Corrosion Treatment recommendations. For preparation of all bonding surfaces it is required to read and understand the instructions given in the Sika AGR Technician Training Manual.

Application

Place cartridge or unipack in a Sika approved oven for a minimum of 1 hour. Product can be heated for a total of 10 hours (either consecutively or in shorter periods adding up to a total of 10 hours).

Cut off the tip of the nozzle in accordance with the vehicle manufacturer's recommendations and screw onto the cartridge or the unipack adapter.

It is recommended to apply the adhesive with a piston-type application gun. To ensure a uniform thickness of adhesive bead, we recommend that the adhesive be applied in the form of a triangular bead (see fig. 1).




Figure 1: Compressing adhesive bead to final size

Removal

Uncured SikaTack® ASAP+ can be removed from tools and equipment with mineral spirits or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin should be washed immediately using a suitable industrial hand cleaner and water. Strictly follow solvent manufacturer's instructions for use and warnings. Do not use solvents on skin!

Application Limits

- Avoid contact with alcohol and alcohol containing solvents during cure.
- Do not apply on frozen surfaces, through standing water, or on wet surfaces.
- Do not apply over silicones or in the presence of curing silicones.
- Glass parts must always be installed within the open time. The open time is significantly shorter in hot and humid climate as well as in temperatures below 40°F. Never install any glass part after the product has built a skin.
- Always use in conjunction with Sika® Aktivator PRO or Sika® Primer-207.

FURTHER INFORMATION

Advice on specific applications will be given on request. To contact Sika Corporation's Industry Technical Services Department please send an email to tsmh@us.sika.com. Copies of the following publications are available on our website www.sikaindustry.com:

- Safety Data Sheets
- Product Data Sheets
- Sika AGR Technician Training Manual

PACKAGING INFORMATION

Cartridge	300 ml
Unipack	465 ml

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LIMITED PRODUCT WARRANTY

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, label and Safety Data Sheet which are available at <http://usa.sika.com/> or on request at tsmh@us.sika.com. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Product Data Sheet, label and Safety Data Sheet prior to product use.

PRODUCT DATA SHEET
SikaTack® ASAP+
Version 01.01 (06 - 2018), en_US
012002210050001100

Sika Corporation
30800 Stephenson Highway
Madison Heights, MI 48071
U.S.A.
Telephone: +1 248-577-0020
Email: tsmh@us.sika.com
www.sikausa.com

